



op papirna

OP polar bright®

* Values presented in above table are indicative



Technical data*	Unit	Standard	OPB37	OPB40	OPB45	OPB50	OPB60
Substance	g/m ²	ISO 536	37	40	45	50	60
Basis weight	lbs	25"x38"/500	25	27	30,5	34	40,5
Caliper	µm	ISO 534	44,5	48	54	60	72
UV Brightness (D65)	%	ISO 2470-2	104	104	104	104	104
CIE Whiteness		ISO 11475	130	130	130	130	130
Opacity	%	ISO 2471	79	81	82	84	87
Roughness	ml/min	ISO 8791-2	<250	<250	<250	<250	<250
Tear resistance CD	mN	ISO 1974	180	200	220	240	280
Tensile strength	kN/m	ISO 1924-2	2,0	2,1	2,4	2,7	3,2
Luminescence		Laetus	10	10	10	10	10



Delfortgroup, proud members of PPLA (Pharmaceutical Printed Literature Association)